



- water pigment paste “VOC FREE”, based in inorganic and organic pigments;
- selection of pigments for tinting systems, with high weathering fastness, compatible with acrylic, vinyl veova, siloxan, silicate, acrylic stirene paints, etc.
- color formulation software/ personal colorcards;
- are suitable to be used “IN PLANT” or “POS” by weight or volume



References	Application	C.I.	Density	Pig. conc. %	Weather resistance			Light Fastness		
					tom cheio	1/3 TiO	1/25 TiO	tom cheio	1/3 TiO	1/25 TiO
Y184	Ext	PY184	1,72	49%	5	5	5	5	8	8
Y74	Int  Ext	PY74	1,13	31%	4	2- 3	2- 3	4	6	6
Y155	Ext	PY155	1,14	35%	4- 5	4	4	4- 5	7- 8	7- 8
Y42	Int  Ext	PY42	1,67	50%	5	5	5	5	8	8
O73	Int  Ext	PO73	1,15	38%	4- 5	4	4	4- 5	7- 8	7
R101	Int  Ext	PR101	1,95	56%	5	5	5	5	8	8
R168	Ext	PR168	1,22	28%	5	5	5	5	8	8
R254	Int  Ext	PR254	1,21	35%	4- 5	4	8	4- 5	7- 8	7
R122	Int  Ext	PR122	1,14	26,5%	5	4- 5	4	5	7- 8	7
V23	Int  Ext	PV23	1,14	28%	4- 5	4	8	4- 5	7- 8	7
B28	Ext	PB28	1,74	60%	5	5	5	5	8	8
B15	Int  Ext	PB15:3	1,23	42%	5	4- 5	4- 5	5	8	8
UMBAR	Int  Ext	Mix	1,48	43%	5	5	5	5	8	8
G07	Int  Ext	PG7	1,31	40%	5	4- 5	4- 5	5	8	8
B07	Int  Ext	PB7	1,18	25%	5	5	5	5	8	8
W06	Int  Ext	PW6	1,86	62%	5	5	5	5	8	8